



ZHONGDING

LAILA

95%TENCEL™LYOCELL 5%CASHMERE

2/60Nm 2/80Nm

LAILA


95% TENCEL™ LYOCCELL 5% CASHMERE

2/60Nm 2/80Nm

天丝™莱赛尔 | 轻垂柔滑

TENCEL™ Lyocell | Light and Drapey

A




BUFF
TC10001

B



WHITE
TC10004★

C




FOGGY
TC10007



SAND
TC10002




AZURE
TC10005



NAVY
TC10008



CACTUS
TC10003



PINK
TC10006



BLACK
TC10009★



ZHONGDING

Please be advised that the color codes have been updated.
Kindly refer to the table below for the latest color codes.

Color Code	Column#	Color Code	Column#	Color Code	Column#
TC10001	A1	TC10004★	B1	TC10007	C1
TC10002	A2	TC10005	B2	TC10008	C2
TC10003	A3	TC10006	B3	TC10009★	C3

注：带有"★"标记的色号表示同时具备2/60Nm和2/80Nm的纱线库存。

Note: Color codes marked with "★" indicate that both 2/60Nm and 2/80Nm yarns are available in stock.



LAILA

成份：95%天丝™莱赛尔
5%山羊绒

支数：2/60Nm
2/80Nm

编织：横机16针-18针
横机16针-18针

后整理： 在两次洗缩过程中,使用专用助剂可以获得更佳的手感。第一次水洗旨在清除纺纱时使用的和毛油助剂和染色过程中遗留的浮色。第二次洗涤主要用于调整织物的手感。

水温: 35°C

浴比: 1:25

第一次水洗：

- ◆ 根据衣服的重量，加入1%非离子助剂
- ◆ 浸泡10分钟
- ◆ 漂洗及脱水

第二次水洗：

- ◆ 根据衣服的重量，加入2%的助剂
- ◆ 浸泡30分钟，转动2-3分钟，可根据需要适当增减转动时间以满足手感要求
- ◆ 脱水
- ◆ 70-75°C标准转笼烘干(浅亮色建议 60°C)

最佳染色量： 3,5,6,10,20,25,50,150,180,250,280,300,400,500,600,700,1000KG/缸

色牢度： 若选用颜色对比强烈的条纹织物，请注意特别的色牢度要求

备注：

色卡所有颜色均可提供样纱服务：素色每色不超3KG，夹花色每色不超 20KG

带有"★"标记的色号表示同时具备2/60Nm和2/80Nm的纱线库存

除夹花色以外，素色均可绞染

客户定纺素色或夹花色最低起订量为每色20KG

素色或夹花色定纺20-50KG，每色额外收取附加费20%



手洗



请勿漂白



低温熨烫



干洗



平摊晾干

COMPOSITION: 95%TENCEL™Lyocell
5%Cashmere

COUNT: 2/60Nm
2/80Nm

GAUGE: Knitting F.16-18
Knitting F.16-18

RECOMMENDED FINISHING:

Utilizing specialized detergent during the two bath processes can enhance the handle. The initial wash aims at removing sizing agents, spin finishes, and residual dyestuffs from the dyeing and spinning processes,while the subsequent wash aims to enhance the handfeel of the fabric.

Water temperature:35°C

Liquor ratio: 1:25

BATH 1:

- ◆ Add 1% non-ionic agent according to the weight of the garment
- ◆ Soak for 10 minutes
- ◆ Rinse and drain

BATH 2:

- ◆ Add 2% of detergent according to the weight of the garment
- ◆ Soak for 30 minutes and rotate for 2-3 minutes, adjusting the rotation time as required to achieve the desired handfeel
- ◆ Drain
- ◆ Standard tumble dry at 70-75°C(60°C recommended for light shades)

OPTIMAL QUANTITY: 3,5,6,10,20,25,50,150,180,250,280,300,400,500,600,700,1000KG/BATCH

COLOUR FASTNESS:

For contrasting striped fabrics, please adhere to specific color fastness requirements

REMARKS:

Sample yarn service available for all colors in colorcard. Solid colors max. 3KG/color ; Melange color max. 20KG/color

Color codes marked with "★" indicate that both 2/60Nm and 2/80Nm yarns are available in stock

Except for the Melange,all the Solid colors can be yarn dyed

MOQ for customer own Solid or Melange color is 20KG/color

Additional charge for customer own color: 20% for 20-50KG/Solid or Melange color



Hand wash



Do Not Bleach



Iron Low



Dry Clean



Dry Flat

CHINA OFFICE

- **Zhejiang Zhongding Textile Co., Ltd.**
No. 388 Zhongshan Road, Chongfu Industrial Zone,
Tongxiang City, Zhejiang Province, China
TEL: +86 573 8822 8888
EMAIL: service@zdtex.com

HONG KONG OFFICE

- **Zhongding International Development Ltd.**
Room 1007, 10/F Saxon Tower,
7 Cheung Shun Street, Lai Chi Kok,
Kowloon, Hong Kong
TEL: +852 3565 5216
EMAIL: matthew@zdtex.com

JAPAN OFFICE

- **Italo.fil**
5-17-6 Minami Aoyama,
Minato-Ku, Tokyo 107-0062, Japan
TEL: +34 609 804 641
EMAIL: nakamura@italo-fil.co.jp

UNITED KINGDOM OFFICE

- **Zhong Ding Int (UK) Company Ltd.**
54, Chaveney Road,
Quorn, Leicestershire,
LE12 8AD, UK
TEL: +44 780 327 7088
EMAIL: richard@zdint.co.uk

GERMANY OFFICE

- **Zhong Ding Int GmbH.**
Stolco Haus, DFC Dialog Büro,
Steinstraße 16-18,
Düsseldorf, D-40212, Germany
TEL: +39 348 155 3609
EMAIL: richard@zdint.co.uk

SPAIN OFFICE

- **Zhong Ding Int.**
Via Augusta 236, 5B,
08021 Barcelona, Spain
TEL: +34 609 804 641
EMAIL: sara@zdint.co.uk