

ZHONG/ /DING

SHEEN

35%EXTRAFINE MERINO WOOL 35%VISCOSE 30%InResST®RECYCLED NYLON

2/48Nm 2/60Nm

19.5µm 丝光羊毛
19.5µm Mercerized Wool

InResST®再生锦纶
InResST® Recycled Nylon

可轻柔机洗
Gentle Machine Washable

SHEEN

2/48Nm 2/60Nm

35%超细美丽诺羊毛 35%粘胶 30%InResST®再生锦纶

35%Extrafine Merino Wool 35%Viscose 30%InResST® Recycled Nylon

SHEEN



成份：
35%超细美丽诺羊毛*
35%粘胶
30%InResST® 再生锦纶

*19.5µm 丝光羊毛

支数及颜色：
2/48Nm - 14/16针 - 30 色
2/60Nm - 16/18针 - 3 色



了解更多

Composition:
35%Extrafine Merino Wool*
35%Viscose
30%InResST®Recycled Nylon

*19.5µm Mercerized Wool

Count & Color:
2/48Nm - 14/16gg - 30 Colors
2/60Nm - 16/18gg - 3 Colors



Learn More

后整理：
在两次洗缩过程中，使用专用助剂可以获得更佳的手感。第一次水洗旨在清除纺纱时使用的和毛油和染色过程中遗留的浮色。第二次洗涤主要用于调整织物的手感。以下后整理方法只供参考，可根据需要的手感调整洗涤剂用量、浸泡时间及转动时长。

水温：30°C **浴比：**1:25

第一次水洗：
根据衣物重量加入1%的洗涤剂，浸泡3分钟后转动1分钟，最后进行漂洗及脱水。

第二次水洗：
根据衣物重量加入2%的柔软剂，浸泡30分钟后转动2-3分钟。最后进行脱水，并在75-80°C下标准转笼烘干（浅亮色衣物建议60°C）。

色牢度：
若选用颜色对比强烈的条纹织物，请注意特别的色牢度要求。

备注：
纱线支数差异可能导致色差，颜色以实物为准。
色卡内所有颜色均可提供样纱服务。
客户色散毛染色最低起订量为20KG/色；订单量低于50KG/色将加收收取20%附加费。

Recommended Finishing:
For optimal handfeel, use the specialized detergent in the two-bath process. The first bath is aimed at removing spin finishes, sizing agents, and residual dyestuffs, while the subsequent bath refines the final fabric handfeel. The following parameters are for reference only; Adjust detergent dosage, soaking and rotation time based on the desired handfeel.

Water Temperature: 30°C **Liquor Ratio:** 1:25

First Wash:
Add 1% detergent by garment weight. Soak for 3 minutes, then rotate for 1 minute. Finally, rinse and spin.

Second Wash:
Add 2% softener by garment weight. Soak for 30 minutes, then rotate for 2-3 minutes. Spin and standard tumble dry at 75-80°C (60°C is recommended for bright/light colors).

Color Fastness:
For fabrics with high-contrast stripes, please pay attention to colorfastness requirements.

Remarks:
Color may vary with yarn count. Please refer to the actual product for the final color.
Sample yarn service is available for all colors on the colorcard.
MOQ for custom color in fiber dyeing: 20KG/color. Orders below 50KG/color will incur a 20% surcharge.


SHEEN

2/48Nm 35%EXTRAFINE MERINO WOOL 35%VISCOSE 30%InResST®RECYCLED NYLON


16gg



ZHONGDING



A



LIMESTONE
N0001

B



MILKY
N0006★


C



CHEESE
N0011




STORM
N0002



RATTAN
N0007




TOFFEE
N0012




GRANITE
N0003★




PEANUT
N0008



CEDAR
N0013



GREASE
N0004



MOSS
N0009



ELM
N0014



OBSIDIAN
N0005★



ROOT
N0010




DEEP FOREST
N0015




ZHONGDING

D



SHORE
N0016

E




ROSE WATER
N0021

F




CREPE
N0026



SKY
N0017



NEBULAR
N0022



BOUQUET
N0027



JUNIPER
N0018



SUGAR PLUM
N0023



CHILI PASTE
N0028



NEPTUNE
N0019



CYBERPUNK
N0024



PALACE
N0029



ANCHOR
N0020



DEEP PURPLE
N0025



LEATHER
N0030



ZHONGDING

SHEEN

New Color Code	Original Color Code	Column#	New Color Code	Original Color Code	Column#	New Color Code	Original Color Code	Column#
N0001	ZP710876	A1	N0011	ZP110885	C1	N0021	ZP410895	E1
N0002	ZP710877	A2	N0012	ZP120886	C2	N0022	ZP610896	E2
N0003★	ZP720878★	A3	N0013	ZP220887	C3	N0023	ZP630897	E3
N0004	ZP730879	A4	N0014	ZP220888	C4	N0024	ZP630898	E4
N0005★	ZP740880★	A5	N0015	ZP230889	C5	N0025	ZP330899	E5
N0006★	ZP010881★	B1	N0016	ZP510890	D1	N0026	ZP410900	F1
N0007	ZP311195	B2	N0017	ZP520891	D2	N0027	ZP420901	F2
N0008	ZP320882	B3	N0018	ZP520892	D3	N0028	ZP430902	F3
N0009	ZP320883	B4	N0019	ZP530893	D4	N0029	ZP430903	F4
N0010	ZP330884	B5	N0020	ZP530894	D5	N0030	ZP330904	F5

★ 提供 2/48Nm 及 2/60Nm 支数 | Available in both 2/48Nm & 2/60Nm yarn counts.

认证与品牌素材支持
Certification & Brand Materials Support



纱线认证
Yarn Certification



其他认证
Other Certifications



支持选用指定原料进行定制
Customization available with specified materials



供应商吊牌
Supplier Hangtag



防伪吊牌 | 可轻柔机洗羊毛
Authenticity Hangtag
Gentle Machine Washable Wool

CHINA OFFICE

- **Zhejiang Zhongding Textile Co., Ltd.**
No. 198, Hangfu Road, Chongfu Industrial Park,
Tongxiang City, Zhejiang
TEL: +86 573 8822 8888
EMAIL: service@zdtex.com

HONG KONG OFFICE

- **Zhong Ding International Development Ltd.**
Room 1007, 10/F Saxon Tower,
7 Cheung Shun Street, Lai Chi Kok,
Kowloon, Hong Kong
TEL: +852 3565 5216
EMAIL: matthew@zdtex.com

JAPAN OFFICE

- **Italo-Fil Co., Ltd.**
Aoyama Green Heights 205
5-17-6 Minami Aoyama,
Minato-Ku, Tokyo 107-0062, Japan
TEL: +03 5464 2577
EMAIL: nakamura@italo-fil.co.jp

USA OFFICE

- **Zhong Ding USA**
525 7th Avenue, Suite 1008
New York, NY 10018
TEL: +917 345 9630
EMAIL: paolo.fontana@aeffefilati.com

UK OFFICE

- **Zhong Ding Int (UK) Company Ltd.**
54, Chaveney Road,
Quorn, Leicestershire,
LE12 8AD, UK
TEL: +44 780 327 7088
EMAIL: richard@zdint.co.uk

GERMANY OFFICE

- **Zhong Ding Int GmbH.**
Stolco Haus, DFC Dialog Büro,
Steinstraße 16-18,
Düsseldorf, D-40212, Germany
TEL: +39 348 155 3609
EMAIL: richard@zdint.co.uk

SPAIN OFFICE

- **Zhong Ding Int.**
Via Augusta 236, 5B,
08021 Barcelona, Spain
TEL: +34 609 804 641
EMAIL: sara@zdint.co.uk