

ZHONG/ /DING

SERENITY

100%UNDYED CASHMERE

2/26Nm

天然无染色山羊绒
Natural Undyed Cashmere

每公斤纱线碳足迹
Carbon Footprint per KG of Yarn
51.9300 kgCO₂e

SERENITY

2/26Nm
100%ECO山羊绒
100%Undyed Cashmere

SERENITY



手洗
Hand Wash



请勿漂白
No Bleach



低温熨烫
Iron Low



干洗
Dry Clean



平摊晾干
Dry Flat

成份：

100%ECO山羊绒

支数及颜色：

2/26Nm - 12针 - 10 色



了解更多

后整理：

在两次洗缩过程中，使用专用助剂可以获得更佳的手感。第一次水洗旨在清除纺纱时使用的和毛油和染色过程中遗留的浮色。第二次洗涤主要用于调整织物的手感。以下后整理方法只供参考，可根据需要的手感调整洗涤剂用量、浸泡时间及转动时长。

水温：35°C **浴比：**1:25

第一次水洗：

根据衣物重量加入2%的蓬松剂，浸泡30分钟后转动6-10分钟，最后进行漂洗及脱水。

第二次水洗：

根据衣物重量加入4%的柔软剂，浸泡20分钟后适时转动。最后进行漂洗及脱水，并在75°C下标准转笼烘干（浅亮色衣物建议60°C）。

色牢度：

若选用颜色对比强烈的条纹织物，请注意特别的色牢度要求。

备注：

色卡内所有颜色均可提供样纱服务。

订单量低于50KG/色将加收20%附加费。

客户特殊色具体起订量及附加费请洽业务部门咨询。

Composition:

100%Undyed Cashmere

Count & Color:

2/26Nm - 12gg - 10 Colors



Learn More

Recommended Finishing:

For optimal handfeel, use the specialized detergent in the two-bath process. The first bath is aimed at removing spin finishes, sizing agents, and residual dyestuffs, while the subsequent bath refines the final fabric handfeel. The following parameters are for reference only; Adjust detergent dosage, soaking and rotation time based on the desired handfeel.

Water Temperature: 35°C **Liquor Ratio:** 1:25

First Wash:

Add 2% fluffy agent by garment weight. Soak for 30 minutes, then rotate for 6-10 minutes. Finally, rinse and spin.

Second Wash:

Add 4% softener by garment weight. Soak for 20 minutes, then rinse and spin. Standard tumble dry at 75°C (60°C is recommended for bright/ light colors).

Color Fastness:

For fabrics with high-contrast stripes, please pay attention to colorfastness requirements.

Remarks:

Sample yarn service is available for all colors on the colorcard.

Orders below 50KG/color will incur a 20% surcharge.

Regarding the MOQ & surcharge for special colors, please contact our sales representative.

A



RESTORE
C30001

B



SKIN
C30006



APPLE CINNAMON
C30002



GRAY SAND
C30007



RAW ALMOND
C30003



WINTER DAWN
C30008



ZHONGDING

C



HEMP
C30004•

D



CAMEL
C30009•



CEMENT
C30005



PIER
C30010✪



ZHONGDING

SERENITY

ColorCode	Column#	ColorCode	Column#
C30001•	A1	C30006☼•	B1
C30002•	A2	C30007•	B2
C30003☼	A3	C30008☼•	B3
C30004•	C1	C30009•	D1
C30005	C2	C30010☼	D2

"•" 大货库存色 Available for bulk stock

"☼" AB纱 Marl yarn

认证与品牌素材支持

Certification & Brand Materials Support



其他认证
Other Certifications



支持选用指定原料进行定制
Customization available with specified materials



防伪吊牌 | 奢华山羊绒
Authenticity Hangtag
Premium Cashmere

CHINA OFFICE

- **Zhejiang Zhongding Textile Co., Ltd.**
No. 198, Hangfu Road, Chongfu Industrial Park,
Tongxiang City, Zhejiang
TEL: +86 573 8822 8888
EMAIL: service@zdtex.com

HONG KONG OFFICE

- **Zhong Ding International Development Ltd.**
Room 1007, 10/F Saxon Tower,
7 Cheung Shun Street, Lai Chi Kok,
Kowloon, Hong Kong
TEL: +852 3565 5216
EMAIL: roxanewoo@zdtex.com

JAPAN OFFICE

- **Italo-Fil Co., Ltd.**
Aoyama Green Heights 205
5-17-6 Minami Aoyama,
Minato-Ku, Tokyo 107-0062, Japan
TEL: +03 5464 2577
EMAIL: nakamura@italo-fil.co.jp

USA OFFICE

- **Zhong Ding USA**
525 7th Avenue, Suite 1008
New York, NY 10018
TEL: +917 345 9630
EMAIL: paolo.fontana@aeffefilati.com

UK OFFICE

- **Zhong Ding Int (UK) Company Ltd.**
54, Chaveney Road,
Quorn, Leicestershire,
LE12 8AD, UK
TEL: +44 780 327 7088
EMAIL: richard@zdint.co.uk

GERMANY OFFICE

- **Zhong Ding Int GmbH.**
Stolco Haus, DFC Dialog Büro,
Steinstraße 16-18,
Düsseldorf, D-40212, Germany
TEL: +39 348 155 3609
EMAIL: richard@zdint.co.uk

SPAIN OFFICE

- **Zhong Ding Int.**
Via Augusta 236, 5B,
08021 Barcelona, Spain
TEL: +34 609 804 641
EMAIL: sara@zdint.co.uk